

SOUND OF COLOR

Modular Tile

Construction

Tufted, Textured Loop, Cut Pile

Tile Size

25 cm x 1 m (9.84" x 39.4")

1 m x 1 m (39.4" x 39.4")

Yarn Type

Milliken-Certified WearOn® Nylon

Stain Resist / Soil Release

StainSmart®

Dye Method

PrintWorks™ Precision Dyeing

Tufted Face Weight

16.3 oz/yd² (552.7 g/m²)

Gauge

1/12

Stitches Per Inch

9.5

Tufts

114/in² (1,766/100 cm²)

Finished Pile Thickness

0.112" (2.84 mm)

Average Density (Finished)

5,300

Standard Backing

PVC-Free WellBAC® Comfort Cushion

Available with TractionBack®

Recycled Content by Total Weight

Standard Backing: 52.0% Pre-Consumer, 3.1% Post-Consumer
NSF 140 Platinum Backing Option: 40.9% Pre-Consumer, 14.2% Post-Consumer

Embodied Carbon

11.74 (kg CO₂e)/m²

Nominal Total Thickness

0.33" (8.4 mm)

Nominal Total Weight

96.9 oz/yd² (3,286 g/m²)

Flammability (Radiant Panel)

ASTM-E-648

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)

≤ 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20% R.H., 70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Heavy

Recommended Maintenance

MilliCare® Textile and Carpet Care Service Network

Indoor Air Quality—CRI Green Label Plus™

GLP0793, Carpet Category 5Y

Recommended Installation Method(s)

Tile: Horizontal Ashlar

Plank: Vertical Ashlar

WARRANTIES

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing


Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel

Flammability



Declare.



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.